**江苏斯尔邦石化有限公司**
*JiangSu Sierbang Petrochemical Co.,Ltd.*
*Tel:886-0518-81391500*
*Fax:0518-81393070*
*Website:www.shenghongpec.com*
*Email:evaxiaoshou@shenghongpec.com*
*PC:222065*
*地址：江苏省连云港市徐圩新区港前大道*
*Address:Gangqian Road,Xuwei New Area,Lianyungang City,Jiangshu Province,China*

斯尔邦石化 SIERBANG PETROCHEMICAL

# EVA

## 特性 Characteristics

**UE28150** 为乙烯-醋酸乙烯酯共聚物，由 Basell 釜式法工艺生产，柔软性佳，粘着性优异，耐低温性良好，相容性良好，热稳定性佳等。

UE28150 is an ethylene-vinyl acetate copolymer (EVA), produced by Autoclave process licensed by Basell. It offers super characteristics,included: good flexibility,excellent adhesion,good low temperature resietance,good compatibility,good thermal stability.

## 应用 Applications

热熔胶 Hot melt adhesives

## 性能 Properties

| 项目 Item | 单位 Unit | 典型值 Typical Value | 测试方法 Test Method |
|---|---|---|---|
| VA 含量 VA Content | wt.% | 28 | GB/T 30925 |
| 熔体质量流动速率 Melt Flow Rate | g/10min | 150 | Sierbang method |
| 拉伸断裂应力 Tensile Strength at Break | MPa | 3.4 | GB/T 1040 |
| 拉伸断裂应变 Tensile Stain at Break | % | 810 | GB/T 1040 |
| 环球软化点 Ring and Ball Softening Temperature | ℃ | 90 | GB/T 15332 |
| 熔融峰温 Peak Melting Temperature | ℃ | 66 | GB/T 19466 |

*上述指标为实验室典型数据，斯尔邦石化公司保证以上数据真实准确，仅用于应用参考，不应该以此作为标准规格。使用上述信息，所发生的一切责任概与本公司无关，所有风险应由用户自行承担。*

*The data listed here is intended to provide typical values and to recommend product applications, should not be used to establish specification limits. Users are responsible for determine whether our product and data are suitable for their particular purpose and for the compliance with related law. The data contained herein is true and accurate. However, since conditions of use are beyond our control, Sierbang assumes no obligation or liability for the data in this document.*